

IPC-4101 /21 /24 /26 UL - File Number E41625

FR406 sets the industry standard for high performance epoxy materials.

PRODUCT FEATURES

Industry Recognition

- UL File Number: E41625
- RoHS Compliant

Processing Advantages

- FR-4 process compatible
- UV blocking and AOI fluorescence
- No post bake after pressing

PRODUCT AVAILABILITY

Standard Material Offering: Laminate

- 2 to 125 mil (0.05 to 3.2 mm)

Copper Foil Type

- HTE Grade 3
- RTF (Reverse Treat Foil)

Copper Weight

- ½, 1 and 2 oz (18, 35 and 70 µm) available
- Thinner copper foil available

Standard Material Offering: Prepreg

- Tooling of prepreg panels

Glass Fabric Availability

- E-glass
- Square weave glass
- Mechanically spread glass

This product is engineered to meet the demands of the multilayer printed circuit board industry, while maintaining standard FR-4 processing. FR406 offers improved dimensional control, superior chemical and thermal performance and product consistency.

PRODUCT ATTRIBUTES



ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye Road Chandler,
AZ 85226 Phone: 480-893-6527
Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd.12/F,
Kin Sang Commercial Centre,
49 King Yip Street, Kwun Tong,
Kowloon,
Hong Kong Phone: 852-2418-1318
Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren,
Germany Phone: 49-2421-8080
Fax: 49-2421-808164

Typical Values Table

Property		Typical Value	Units		Test Method
			Metric (English)	IPC-TM-650 (or as noted)	
Glass Transition Temperature (Tg) by DSC		170		°C	2.4.25C
Decomposition Temperature (Td) by TGA @ 5% weight loss		300		°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	10 >2		Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	60 250 3.5		ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE	Pre-Tg	13		ppm/°C	2.4.24C
Thermal Conductivity		0.3-0.4		W/m-K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass		Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 100 MHz	4.00		—	2.5.5.3
	B. @ 1 GHz	3.95			2.5.5.9
	C. @ 2 GHz	3.93			2.5.5.5
	D. @ 5 GHz	3.92			2.5.5.5
	E. @ 10 GHz	3.92			2.5.5.5
Df, Loss Tangent	A. @ 100 MHz	0.0130		—	2.5.5.3
	B. @ 1 GHz	0.0161			2.5.5.9
	C. @ 2 GHz	0.0167			2.5.5.5
	D. @ 5 GHz	0.0172			2.5.5.5
	E. @ 10 GHz	0.0172			2.5.5.5
Volume Resistivity	A. C-96/35/90	9.0×10^7		MΩ-cm	2.5.17.1
	B. After moisture resistance	—			
	C. At elevated temperature	3.0×10^7			
Surface Resistivity	A. C-96/35/90	3.0×10^8		MΩ	2.5.17.1
	B. After moisture resistance	—			
	C. At elevated temperature	8.0×10^8			
Dielectric Breakdown		>50		kV	2.5.6B
Arc Resistance		90		Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		44 (1100)		kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		3 (175-249)		Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil]	1.19 (7.0)		N/mm (lb/inch)	2.4.8C
	B. Standard profile copper	1.60 (9.0)			2.4.8.2A
	1. After thermal stress	1.19 (7.0)			2.4.8.3
	2. At 125°C (257°F)	1.60 (9.0)			2.4.8.3
Flexural Strength	A. Length direction	646 (93.7)		MPa (kpsi)	2.4.4B
	B. Cross direction	539 (78.2)			
Tensile Strength	A. Length direction	434 (63.0)		MPa (kpsi)	ASTM D3039
	B. Cross direction	329 (47.7)			
Young's Modulus	A. Length direction	3684		ksi	ASTM D790-15e2
	B. Cross direction	3116			
Poisson's Ratio	A. Length direction	0.191		—	ASTM D3039
	B. Cross direction	0.154			
Moisture Absorption		0.2		%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0		Rating	UL 94
Relative Thermal Index (RTI)		130		°C	UL 796

NOTES

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B: Corrected units for Flexural and Tensile Strength - 8/18

C: Change MOT to RTI 5/19

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.