

IPC-4101 /98 /99 /101 /126 UL - File Number E41625

FR408HR is a high-performance FR-4 resin system with a 230°C (DMA) Tg for multilayer PCB applications where maximum thermal performance and reliability are required.

### PRODUCT FEATURES

#### Industry Recognition

- RoHS Compliant

#### Performance Attributes

- CAF resistant
- Lead-free assembly compatible
- 6x 260°C reflow capable
- 6x 288°C solder float capable

#### Processing Advantages

- FR-4 process compatible
- Via filling capability
- Multiple lamination cycles

### PRODUCT AVAILABILITY

#### Standard Material Offering: Laminate

- 2 to 30 mil (0,05 to 0.75 mm)

#### Copper Foil Type

- HTE Grade 3
- RTF (Reverse Treat Foil)
- Embedded resistor foil

#### Copper Weight

- ½, 1 and 2 oz (18, 35 and 70 µm) available
- Heavier copper foil available
- Thinner copper foil available

#### Standard Material Offering: Prepreg

- Tooling of prepreg panels

#### Glass Fabric Availability

- E-glass
- Square weave glass
- Mechanically spread glass

FR408HR laminate and prepreg products are manufactured with Isola’s patented high performance multifunctional resin system, reinforced with electrical grade (E-glass) glass fabric. This system delivers a 30% improvement in Z-axis expansion and offers 25% more electrical bandwidth (lower loss) than competitive products in this space. These properties coupled with superior moisture resistance at reflow, result in a product that bridges the gap from both a thermal and electrical perspective.

The FR408HR system is also laser fluorescing and UV blocking for maximum compatibility with Automated Optical Inspection (AOI) systems, optical positioning systems and photo-imagable solder mask imaging.

### PRODUCT ATTRIBUTES



### TYPICAL MARKET APPLICATIONS



**ORDERING INFORMATION:**

Contact your local sales representative or contact [info@isola-group.com](mailto:info@isola-group.com) for further information.

**Isola Group**  
6565 West Frye Road Chandler,  
AZ 85226 Phone: 480-893-6527  
Fax: 480-893-1409

**Isola Asia Pacific**  
(Hong Kong) Ltd. 12/F,  
Kin Sang Commercial Centre,  
49 King Yip Street, Kwun Tong,  
Kowloon,  
Hong Kong Phone: 852-2418-1318  
Fax: 852-2418-1533

**Isola GmbH**  
Isola Strasse 2 D-52348 Düren,  
Germany Phone: 49-2421-8080  
Fax: 49-2421-808164

# Typical Values Table

Property	Typical Value	Units		Test Method
		Metric (English)	IPC-TM-650 (or as noted)	
Glass Transition Temperature (Tg) by DSC	190	°C	2.4.25C	
Decomposition Temperature (Td) by TGA @ 5% weight loss	360	°C	2.4.24.6	
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	60 >30	Minutes 2.4.24.1	
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	55 230 2.8	ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE	Pre-Tg	16	ppm/°C	2.4.24C
Thermal Conductivity		0.4	W/m-K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	3.72 3.69 3.68 3.64 3.65	—	2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Df, Loss Tangent	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	0.0072 0.0091 0.0092 0.0098 0.0095	—	2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Volume Resistivity	A. After moisture resistance B. At elevated temperature	$4.4 \times 10^7$ $9.4 \times 10^7$	MΩ-cm	2.5.17.1
Surface Resistivity	A. After moisture resistance B. At elevated temperature	$2.6 \times 10^6$ $2.1 \times 10^8$	MΩ	2.5.17.1
Dielectric Breakdown		>50	kV	2.5.6B
Arc Resistance		137	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		70 (1741)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		2 (250-399)	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil] B. Standard profile copper 1. After thermal stress 2. After process solutions	1.14 (6.5) 0.96 (5.5) 0.90 (5.1)	N/mm (lb/inch)	2.4.8C 2.4.8.2A 2.4.8.3
Flexural Strength	A. Length direction B. Cross direction	500 (72.5) 400 (58.0)	MPa (kpsi)	2.4.4B
Tensile Strength	A. Length direction B. Cross direction	376 (54.5) 267 (38.7)	MPa (kpsi)	ASTM D3039
Young's Modulus	A. Length direction B. Cross direction	3695 3315	ksi	ASTM D790-15e2
Poisson's Ratio	A. Length direction B. Cross direction	0.137 0.133	—	ASTM D3039
Moisture Absorption		0.061	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		130	°C	UL 796

## NOTES

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B: Corrected units for Flexural and Tensile Strength - 8/18

C: Removed Low Dk Glass Option - 10/18

D: Change MOT to RTI - 5/19

E: Revised CTI to 2 - 1/21

F: Removed "0.8 mm pitch" feature seen as limitation versus capability - 6/24

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.