

IPC-4101 /134 UL - File E41625 Grade PCL-FR-370HR

TerraGreen® 400G laminate materials are our most advanced ultra high speed, halogen free ultra low loss design solutionnargap.

### PRODUCT FEATURES

#### Industry Recognition

- UL File Number: E41625
- RoHS Compliant

#### Performance Attributes

- CAF resistant
- Lead-free assembly compatible
- 6x 260°C reflow capable
- 6x 288°C solder float capable

#### Processing Advantages

- FR-4 process compatible
- Excellent fill and flow for heavy copper
- Multiple lamination cycles
- HDI technology compatible

### PRODUCT AVAILABILITY

#### Standard Material Offering: Laminate

- 2 to 20 mil (0.05 to 0.51 mm)

#### Copper Foil Type

- HVLP3 (VLP1)  $\leq 1.1$  micron Rz JIS

#### Copper Weight

- ½, 1 oz (18 and 35  $\mu\text{m}$ ) available

#### Standard Material Offering: Prepreg

#### Glass Fabric Availability

- Low Dk glass
- Square weave glass
- Mechanically spread glass

TerraGreen® 400G (RF/MW) is our Halogen Free material solution for next generation 5G infrastructure and mmWave applications. Our novel resin system has been engineered for high data rates with excellent cost for loss performance.

TerraGreen® 400G (RF/MW) is lead free compatible and can be processed utilizing standard PCB equipment and processing steps.

TerraGreen® 400G (RF/MW) meets UL 94 V-0 and is halogen free.

### PRODUCT ATTRIBUTES



### TYPICAL MARKET APPLICATIONS



### ORDERING INFORMATION:

Contact your local sales representative or contact [info@isola-group.com](mailto:info@isola-group.com) for further information.

#### Isola Group

6565 West Frye Road Chandler, AZ 85226  
Phone: 480-893-6527  
Fax: 480-893-1409

#### Isola Asia Pacific

(Hong Kong) Ltd. 12/F, Kin Sang Commercial Centre, 49 King Yip Street, Kwun Tong, Kowloon,  
Hong Kong  
Phone: 852-2418-1318  
Fax: 852-2418-1533

#### Isola GmbH

Isola Strasse 2 D-52348 Düren, Germany  
Phone: 49-2421-8080  
Fax: 49-2421-808164

# Typical Values Table

Property	Typical Value	Units		Test Method
		Metric (English)	IPC-TM-650 (or as noted)	
Glass Transition Temperature (Tg) by DSC	200	°C	2.4.25C	
Glass Transition Temperature (Tg) by DMA	215	—	2.4.24.4	
Glass Transition Temperature (Tg) by TMA	180	°C	2.4.24C	
Decomposition Temperature (Td) by TGA @ 5% weight loss	>380	°C	2.4.24.6	
Time to Delaminate by TMA (Copper removed)	T288	60+	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C.	37 170 1.8	ppm/°C	2.4.24C
X/Y-Axis CTE		12/13	ppm/°C	2.4.24C
Thermal Conductivity		0.54	W/m·K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 5 GHz B. @ 10 GHz C. @ 20 GHz	3.07	—	2.5.5.5
Df, Loss Tangent	A. @ 5 GHz B. @ 10 GHz C. @ 20 GHz	0.0018	—	Bereskin Stripline
Peel Strength		0.7 (4.1)	N/mm (lb/inch)	2.4.8C
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		140	°C	—

## NOTES

### Notes:

**All data is preliminary and subject to change**

**\* Data was developed using 55% RC rigid laminate**

Revisions:

A: Preliminary Release

B-Corrected CTE data-5/24

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.